

TECNICAL CHARACTERISTICS	TEST STANDARD UNI EN ISO	PRODUCT STANDARD ISO 13006 EN 14411	AVERAGE VALUES	
DIMENSIONAL CHARACTERISTICS				
Length and width	10545 - 2	+/- 0,6 % (+/- 2 mm)	+/- 0,6 % (+/- 2 mm)	
Thickness		+/- 5 % (+/- 0,5 mm)	+/- 5 % (+/- 0,5 mm)	
Straightness of sides		+/- 0,5 % (+/- 1,5 mm)	+/- 0,5 % (+/- 1,5 mm)	
Rectangularity		+/- 0,5 % (+/- 2 mm)	+/- 0,5 % (+/- 2 mm)	
Surface flatness		+/- 0,5 % (+/- 2 mm)	+/- 0,5 % (+/- 2 mm)	
PHYSICAL PROPERTIES				
Water absorption	10545 - 3	≤ 0,5 %	≤ 0,3 %	
Breaking strength (N)	10545 - 4	min 1300	≥ 1500	
Modulus of rupture (N/mm ²)		min 35	≥ 45	
Resistance to surface abrasion	10545 - 7	Indicated by the manufacturer		
Coefficient of linear thermal expansion (K ⁻¹)	10545 - 8	Test method available	6 x 10 ⁻⁶	
Thermal shock resistance	10545 - 9	Test method available	Resists	
Moisture expansion (mm/m)	10545 - 10	Test method available	< 0,1	
Crazing resistance	10545 - 11	Required	Resists	
Frost resistance	10545 - 12	Required	Resists	
Slip resistance	ASTM C 1028	-	Wet > 0,60; Dry > 0,60	
Slip resistance, DCOF	ANSI.A137.1:2012 BOT 3000	-	> 0,42	
Fire reaction	EN 13823 EN 9239-1	CPR(UE) 305/2011, 2000/147/CE, UNI EN 13501-1	Class A1 _{fl}	
CHEMICAL PROPERTIES				
Resistance to household chemicals and swimming pool salts	10545 - 13	min GB	GA	
Resistant to low concentrations		Acids	Indicated by the manufacturer	GLA
		Alkalis		GLA
Resistant to high concentrations		Acids	Test method available	-
		Alkalis		-
Resistance to stains	10545 - 14	min 3	5	


This product complies with all the requirements that appears in the international Standard ISO 13006:2018 annex B1a and European Standard EN 14411:2016



EN 14411 : 2012

DoP nr. 001 GP

Solignano Nuovo, 05/12/2022


 Technical Department
